

10-24-00



23351

PATENT TRADEMARK OFFICE
PATENT

Practitioner's Docket No. 16039-1

Preliminary Classification:
Proposed Class:
Subclass:

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Box Patent Application
Assistant Commissioner for Patents
Washington, D.C. 20231

NEW APPLICATION TRANSMITTAL

Transmitted herewith for filing is the patent application of

Inventor(s): Ji (nmi) SU; Joycelyn S. HARRISON

For (title): NON-UNIFORM THICKNESS ELECTROACTIVE DEVICE

CERTIFICATION UNDER 37 C.F.R. SECTIONS 1.8(a) AND 1.10*
(When using *Express Mail*, the *Express Mail* label number is **mandatory**;
Express Mail certification is optional.)

I hereby certify that, on the date shown below, this correspondence is being:

MAILING

- ☐ deposited with the United States Postal Service in an envelope addressed to the Assistant Commissioner for Patents, Washington, D.C. 20231.

37 C.F.R. Section 1.8(a)

37 C.F.R. Section 1.10*

- ☐ with sufficient postage as first class mail. ☒ as "Express Mail Post Office to Address"
Mailing Label No. EK161582220
(mandatory)

TRANSMISSION

- ☐ transmitted by facsimile to the Patent and Trademark Office (703) ____-____.

Date: Oct. 23, 2000

Robin W. Edwards
Signature
Robin W. Edwards
(type or print name of person certifying)

***WARNING:** Each paper or fee filed by "Express Mail" **must** have the number of the "Express Mail" mailing label placed thereon prior to mailing. 37 C.F.R. Section 1.10(b).
"Since the filing of correspondence under [Section] 1.10 without the Express Mail mailing label thereon is an oversight that can be avoided by the exercise of reasonable care, requests for waiver of this requirement will **not** be granted on petition." Notice of Oct. 24, 1996, 60 Fed. Reg. 56,439, at 56,442.

10/23/00
JC575 U.S. PTO

10/23/00
JC575 U.S. PTO
23351/60

RECEIVED
OCT 27 2000
OPE/JCW/S

09605526-102300

1. Type of Application

This transmittal is for an original (nonprovisional) application.

2. Papers Enclosed

A. Required for filing date under 37 C.F.R. 1.53(b) (Regular) or 37 C.F.R. 1.153 (Design) Application

11 Page(s) of Specification

5 Page(s) of Claims

4 Sheet(s) of Drawing(s)--Informal

B. Other Papers Enclosed

2 Page(s) of declaration and power of attorney--inventors unavailable for signature

1 Page(s) of Return Postal Card

3. Declaration or Oath

Enclosed

Unexecuted by:

* inventors.

4. Inventorship Statement

The inventorship for all the claims in this application is the same.

5. Language

English

6. Assignment

An assignment of the invention to Administrator, National Aeronautics and Space will follow.

7. **Fee Calculation (37 C.F.R. Section 1.16)**

Regular Application

CLAIMS AS FILED					
Claims	Number Filed	Basic Fee Allowance	Number Extra	Rate	Basic Fee 37 CFR 1.16(a) \$710.00
Total Claims (37 CFR 1.16(c))	35	- 20 =	15 x	\$18.00	\$270.00
Independent Claims (37 CFR 1.16(b))	1	- 3 =	0 x	\$80.00	\$0.00
Multiple Dependent Claim(s), if any (37 CFR 1.16(d))			+	\$270.00	\$0.00
Filing Fee Calculation					\$980.00

8. **Fee Payment Being Made at This Time**

Enclosed	
Filing Fee	\$980.00
Total Fees Enclosed	\$980.00

9. **Method of Payment of Fees**

Charge Account No. 14-0116 in the amount of \$980.00.
A duplicate of this transmittal is attached.

10. **Authorization to Charge Additional Fees**

The Commissioner is hereby authorized to charge the following additional fees by this paper and during the entire pendency of this application to Account No. 14-0116.

37 C.F.R. Section 1.16(a), (f) or (g) (filing fees)
37 C.F.R. Section 1.16(b), (c) or (d) (presentation of extra claims)
37 C.F.R. Section 1.16(e) (surcharge for filing the basic filing fee and/or declaration on a date later than the filing date of the application)
37 C.F.R. Section 1.17(a)(1)-(5) (extension fees pursuant to SECTION 1.136(a))
37 C.F.R. Section 1.17 (application processing fees)
37 C.F.R. Section 1.18 (issue fee at or before mailing of Notice of Allowance, pursuant to
37 C.F.R. Section 1.311(b))

11. Instructions as to Overpayment

Credit Account No. 14-0116.

12. Relate Back

Amend the specification by inserting, before the first line, the following sentence:
N/A

13. Maintenance of Copendency of Prior Application

A. Conditional Petition for Extension of Time in Prior Application
A conditional petition for extension of time is being filed in the pending **prior** application.
N/A

14. Further Inventorship Statement Where Benefit of Prior Application(s) Claimed

Date: Oct. 23, 2000

Robin W. Edwards

Robin W. EDWARDS
Registration No. 39,179
NASA Langley Research Center
3 Langley Boulevard
Mail Stop 212
Hampton, VA 23681-2199
757-864-3230
Customer No. 23351



23351

PATENT TRADEMARK OFFICE

PATENT

Practitioner's Docket No. LAR 16039-1

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re application of: SU, Ji (nmi); HARRISON, Joycelyn S.

Application No.: Group No.:
Filed: Examiner:
For: NON-UNIFORM THICKNESS ELECTROACTIVE DEVICE



Assistant Commissioner for Patents
Washington, D.C. 20231

EXPRESS MAIL CERTIFICATE

"Express Mail" label number EK161582205
Date of Deposit 10/23/2000

I hereby state that the following *attached* paper or fee

NEW UTILITY PATENT APPLICATION

is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 C.F.R. section 1.10, on the date indicated above and is addressed to the Assistant Commissioner for Patents, Washington, D.C. 20231.

ROBIN W. EDWARDS

Robin W. Edwards
Signature of person mailing paper or fee

Return Postal Card
Org & 1 transmittal form
Specification, Claims, Abstract - 17 pgs
Declaration (NASA Form 1538)

**23351**

PATENT TRADEMARK OFFICE

-1-

NON-UNIFORM THICKNESS ELECTROACTIVE DEVICEClaim of Benefit of Provisional Application

5 Pursuant to 35 U.S.C. §119, the benefit of priority from provisional application 60/161,113, with a filing date of October 22, 1999, is claimed for this non-provisional application.

Cross Reference to Related Cases

10

This application is related to co-pending, commonly owned patent application Serial No. _____, filed October 23, 2000, entitled "Polymer-Polymer Bilayer Actuator", co-pending, commonly owned patent application Serial No. _____, filed October 23, 2000, entitled "Electrostrictive Graft
15 Elastomers", and co-pending, commonly owned patent application Serial No. _____, filed October 23, 2000, entitled "Membrane Position Control."

Origin of the Invention

20 The invention described herein was made by an employee of the United States Government and a National Research Council Research Associate and may be used by or for the Government for governmental purposes without the payment of any royalties thereon or therefor.

25 Background of the Invention1. Field of the Invention

30 The present invention is generally related to the field of electroactive actuators. More specifically, it relates to an electroactive actuator having at least one layer of non-uniform thickness.

-2-

2. Description of the Related Art

Actuation devices are used for many applications, including aerospace, fluid flow and biomedical. Space applications include robotics, miniature rovers, and the shaping, tuning, positioning, controlling and deforming of membrane structures. Membrane inflatable and deployable space structures are used by the government and commercially as reflectors, antennas, solar arrays, satellites, solar sails, etc. Although actuation devices are widely used, many challenges exist which limit their performance for high precision applications. Factors affecting precision include surface smoothness, deviation from desired surface profile, surface deformations due to thermal fluctuations, and accurate membrane positioning. Additionally, hydrofoils and airfoils that can optimize their surface shape at varying flow rates are desirable to, for example, increase lift, reduce noise levels, lower vibrations and reduce drag. Other potential uses of actuation devices include precise positioning of display panels and optical index layers. To operate most effectively in the aforementioned applications, actuation devices require sufficient force and strain, and often need to produce complex motions that may include both bending and torsion.

Conventional piezoelectric ceramic, polymer, and composite actuators (including piezoelectric, electrostrictive, and electrostatic) lack the combination of sufficient strain and force to most effectively perform the aforementioned functions. Previous concepts for shaping and tuning membrane structures have primarily involved the use of piezoelectric ceramic materials. These ceramic piezoelectrics have the major problems of large mass, high density, low strain and high brittleness. Generally, piezoceramics also need additional mechanical devices to achieve a shaping, tuning, positioning, controlling or deforming function. In contrast to electroceramics, electroactive polymers are emerging as new actuation materials due to their enhanced strain capabilities.

-3-

Electrostrictive polymer-polymer actuators or other electroactive polymer actuators that provide enhanced strain capabilities can shape, tune, position, control and deform membrane structures, as well as perform in other applications, in ways not previously possible with other materials. An
5 example of such an electrostrictive polymer-polymer actuator is described in the patent application entitled "Polymer-Polymer Bilayer Actuator", Serial No. _____, filed October 23, 2000, hereby incorporated by reference. The greater strain capability provides further possibilities for small-scale applications and integration into skin surfaces. The electroactive actuators
10 can coincide with specific contours to optimize, for example, shapes for fluid flow, reflection and other membrane uses.

Existing devices capable of providing complex motion response utilize surface electrode patterning and/or polymer laminates having tailored lamina properties and orientations, such as described in U.S. Patent Number
15 4,868,447. It is desirable to obtain complex motion response without requiring tailored surface electroding or laminate design.

Statement of the Invention

20 Accordingly, an object of the present invention is to provide an electroactive device having controlled local strain and curvature.

Another object is to provide an electroactive device having a response contour which varies across the device.

Another object is to provide an electroactive device that can produce
25 complex motions.

A further object is to provide an electroactive device with enhanced strain capabilities.

Additional objects and advantages of the present invention are apparent from the drawings and specification that follow.

30

-4-

Summary of the Invention

In accordance with the present invention, the foregoing and other objects and advantages are attained by providing an electroactive device having at least two layers of material, wherein at least one layer is an electroactive material and wherein at least one layer is of non-uniform thickness. The device can be produced in various sizes, ranging from large structural actuators to microscale or nanoscale devices. The applied voltage to the device in combination with the non-uniform thickness of at least one of the layers (electroactive and/or non-electroactive) controls the contour of the actuated device. The effective electrical field is a mathematical function ($E = V/D$, where E is electrical field, V is voltage and D is thickness) of the local layer thickness. Therefore, the local strain and the local bending/torsion curvature are also a mathematical function of the local thickness. Hence the thinnest portion of the actuator offers the largest bending and/or torsion response. Tailoring of the layer thicknesses can enable complex motions to be achieved.

In a preferred embodiment, one or more electroactive layers of non-uniform thickness control the curvature of the device. The most responsive portions of the device will be at the thinnest portions of the electroactive layers, where the highest electric fields result. In other embodiments, the curvature can be controlled by varying the thickness of the non-electroactive layer or by varying the thickness of both the electroactive layer(s) and non-electroactive layer.

The electroactive device described herein will provide enabling technology to allow variable contouring of the device to expand electroactive actuator use in applications such as motion control, position control, tension control, curvature control, biomedical pulse control, surface flow dynamic control, display panels, optical alignment, optical filters, micro-electromechanical systems, and nano-electromechanical systems. More specifically, it can be utilized in membrane inflatable and deployable

-5-

structures, and be used for shaping surfaces such as hydrofoils and airfoils to optimize shape for different flow rates. Furthermore, the device could serve to provide precise positioning of an optical index layer for a liquid crystal display and provide positioning control of display panels to reduce glare.

5 Advantages of using polymers for the electroactive layer(s) include low weight, unified materials-device body, simple operation, long lifetime, flexibility, toughness, and ease of processing. However, use of layers (electroactive and/or non-electroactive) of non-uniform thickness to control the curvature can be applied to any materials that can cooperatively produce
10 a sufficient force and strain combination for particular shaping, tuning, positioning, controlling and deforming applications.

Brief Description of the Drawings

15 A more complete appreciation of the invention and the many of the attendant advantages thereof will be readily attained as the same becomes better understood by reference to the following detailed description when considered in connection with the accompanying drawings, wherein:

 FIGs. 1A illustrates a side view of an embodiment of a non-uniform
20 thickness actuator, showing the most responsive portions located at the thinnest points of the active layer closer to the free end.

 FIG. 1B illustrates a side view of an embodiment of a non-uniform thickness actuator, showing the most responsive portions located at the thinnest points of the active layer closer to the cantilevered end.

25 FIG. 2 illustrates a side view of a non-uniform thickness actuator fixed at one end, with the thickness of the active layer decreasing towards the fixed ends.

 FIGs. 3A-3C illustrate a cross section of a typical hydrofoil or airfoil with a non-uniform thickness actuator, in actuated and non-actuated
30 configurations, attached to the surface of the foil.

-6-

FIG. 3D illustrates a cross section of a typical hydrofoil or airfoil with a non-uniform thickness actuator integrated into the foil.

FIG. 4 illustrates an embodiment of a non-uniform thickness actuator having stacked electroactive layers, wherein the stacks on either side of the bond interface are alternately activated.

FIG. 5 illustrates an embodiment of a non-uniform thickness actuator having multiple electroactive layers.

Detailed Description of the Invention

Referring now to the drawings, and more particularly to FIGs. 1A and 1B, an electroactive device according to the present invention is shown and referenced generally by the numeral 100. Electroactive layer 112 is of non-uniform thickness and is bonded to non-electroactive layer 114, which has uniform thickness. A layer should be understood to be a sheet, strip, film, plate, or the like, which may have various configurations such as planar, annular, and spiral. Although either or both layers can be of nonuniform thickness, nonuniformity of the electroactive layer thickness will produce the greatest strain, and hence displacement capability of the device.

Electroactive layer 112 can be any material that responds to electrical activation, including a polymer, ceramic or composite, and is selected based upon the response desired. A preferred material is the electrostrictive graft elastomer described and claimed in "Electrostrictive Graft Elastomer", Serial No. _____, filed October 23, 2000, hereby incorporated by reference. Another preferred embodiment is the polymer-polymer actuator described and claimed in "Polymer-Polymer Bilayer Actuator", Serial No. _____, filed October 23, 2000, also hereby incorporated by reference, wherein the active polymeric web has non-uniform thickness. Non-electroactive layer 114 must have a mechanical modulus sufficient to obtain the desired response in conjunction with electroactive layer 112. For equal thickness of the electroactive layer 112 and non-electroactive layer

-7-

114, the mechanical modulus of the non-electroactive layer 114 is preferred to be equal to or lower than the mechanical modulus of the electroactive layer 112 in order to achieve maximum bending displacement. Candidate materials include polymers, ceramics, composites, and metals.

5 The layers 112 and 114 are bonded using chemical, physical, mechanical, or biological bonding means. The preferred bonding means provide ease in processing, minimized thickness, as well as the desired stiffness and durability. Especially preferred is a chemical adhesive that is cast and cured at room temperature. The bonding layer thickness depends
10 on the whole configuration of the device, including the material selections for the electroactive and non-electroactive layers, as well as the device's displacement and stress induced at the bonding interfaces. The thinnest bonding layer that satisfies the device requirements is preferred. Epoxy resin is a suitable chemical adhesive.

15 Layers 112 and 114 are fixedly mounted at 116 and electrically connected to a drive voltage (not shown). When no voltage is supplied, the device remains in the non-activated position 120. In Fig. 1A, when voltage is supplied, electrical signals are supplied across the thickness of layer 112, and the electroactive response of layer 112 causes device 100 to bend to
20 position 140. The electrical signals are supplied via one or more electrodes 130 disposed on each of the upper and lower surfaces of layer 112. These electrodes 130 can be disposed via a single layer across the surface or via multiple or patterned electrodes, depending on the desired response. One example of suitable electrodes 130 are gold electrodes, although any
25 material having significant conductivity (generally greater than 10^5 S/m) and fatigue resistance can be used. A conductive polymer having mechanical elasticity comparable to the electroactive material and good adherence to the electroactive material is preferred for the electrode material. Some examples of suitable electrodes are polypyrrole and polyaniline. The drive voltage is
30 dependent on the number of device layers, as well as on the desired displacement, and can range from several volts to several kV.

-8-

The most responsive area of device 100 is position 140 at the thinnest portion of electroactive layer 112. Similarly, in Fig. 1B, the most responsive area of device 100 is position 150, at the the thinnest portion of electroactive layer 112. In other embodiments the non-electroactive layer 114 may be of non-uniform thickness, although lesser displacement of the device would be achieved.

The thickness ratio between electroactive layer 112 and non-electroactive layer 114 can be tailored to achieve the desired response. If the electroactive and non-electroactive layers have the same mechanical modulus, then the non-electroactive layer thickness should be less than or equal to that of the electroactive layer thickness. If the moduli differ, the thicknesses are optimized based on the application requirements. The thickness of the layers 112 and 114 depend upon the desired response. For multiple electroactive layers, the thicknesses of the layers, the moduli of the layers, and the material selection is tailored to achieve desired results.

Referring to FIGs. 2A and 2B, another embodiment of the electroactive device according to the present invention is shown and referenced generally by the numeral 200. Electroactive layer 212 is narrowed at each end and is bonded along its length to non-electroactive layer 214, which has uniform thickness. Device 200 is fixedly attached at 280 to a structure 235 on which the actuator acts. Furthermore, device 200 can be attached to the support layer 235 by chemical or mechanical means. Electroactive layer 212 is electrically connected to a drive voltage (not shown). When no voltage is supplied, as illustrated in FIG. 2A, the device 200 remains in its non-activated position. When voltage is supplied, as illustrated in FIG. 2B, the electroactive response of layer 212 causes device 200 to bend to its activated position. The most responsive areas of the device 200 are at the thinnest portions of layer 212, nearest ends 280 and 290

FIGs. 3A through 3C depict an application in which a non-uniform electroactive device is used to optimize characteristics of a hydrofoil or airfoil. Such optimization may include the formation of traveling waves. Cross-

-9-

section 300 represents a typical airfoil or hydrofoil. One or more non-uniform thickness electroactive actuators 310 are affixed to the airfoil or hydrofoil, preferably at the leading edge. In the activated positions 320 and 330, the actuators form a curvature that alters the flow stream 340. FIG. 3B illustrates the actuator displacement resulting from the actuator being fixed at 350 to the airfoil or hydrofoil. FIG. 3C illustrates an actuator displacement resulting from the actuator being fixed at 360 to the airfoil or hydrofoil. In another embodiment, shown in FIG. 3D, one or more electroactive devices 370 are integrated into the airfoil or hydrofoil; i.e., attached to and recessed within the hydrofoil or airfoil 300. Again, the electroactive devices are affixed at one end to the airfoil or hydrofoil. This embodiment results in a smooth airfoil/hydrofoil surface when the electroactive device(s) 370 are in their inactivated state.

FIG. 4 illustrates an embodiment having multiple electroactive layers 400 through 450. Electroactive layers 400 through 420 form a first stack 470 and electroactive layers 430 through 450 form a second stack 480. The first stack 470 and second stack 480 are bonded via bonding layer 460. First stack 470 and second stack 480 are alternately activated. Although electroactive layers 400 through 450 can be different materials, consistent materials are preferred to obtain greater control of the device.

FIG. 5 illustrates an embodiment having three electroactive layers 510 through 530 and a single non-electroactive layer 500. Such a multiple electroactive layer arrangement may be used to obtain greater output force and greater strain/displacement for a given drive voltage.

The thickness variation of one or more layers is chosen to achieve a desired contour. The thickness of a layer can vary as any function of length, any function of width, or as any function of both length and width. This thickness variation acts in cooperation with and/or enhances the contour that could be achieved by material choice, electrode design, or orientation of layers. The electroactive device

-10-

Although the drawings illustrate specific configurations, the invention is not limited to such specific configurations. At least one electroactive layer is required and at least one non-uniform thickness layer (electroactive or non-electroactive) is required, but each desired application and its associated
5 desired response (strain and force) will dictate the number of electroactive layers and number of nonuniform layers needed. A non-electroactive layer is not required, such as the embodiment shown in FIG. 4 illustrates; however, if a non-electroactive layer is used, there should be no more than one. As provided earlier, such non-electroactive layer may be of uniform or non-
10 uniform thickness depending on the desired results. Although the embodiments shown illustrate the electroactive devices being fixed at an end, they may be fixed to another location as desired for a specific application. For example, the electroactive device itself could be the membrane to be deformed, such as a reflector, and have a centrally fixed point.

15 Factors which affect the performance of the present invention include:

1) the non-uniformity in layer thicknesses; 2) electromechanical properties of the electroactive layer, such as electric field induced strain, mechanical modulus, and electromechanical conversion efficiency, as well as output energy/energy density; 3) mechanical properties of the non-electroactive
20 layer, such as mechanical modulus; 4) bonding between the layers, as well as 5) the geometric dimension of each component. For an optimized configuration; 1) the electroactive layer(s) offer maximized electric field induced strain and maximized mechanical modulus, therefore, maximized electromechanical output power/energy; 2) the non-electroactive layer offers
25 mechanical modulus not higher than that of the electroactive layer(s); 3) the bonding between layers offers strength, does not allow any significant sliding effect between the electroactive and non-electroactive layers in the direction parallel to the surfaces, and offers maximized durability under working conditions; 4) the relative dimensions of the electroactive layer(s) and non-
30 electroactive layer are chosen according to the requirements of a particular application, with a relatively thin non-electroactive layer being preferred; 5)

the thickness of the bonding material is minimized; and 6) the non-uniform thicknesses of layers are designed to meet desired response requirements.

Obviously, numerous additional modifications and variations of the present invention are possible in light of above teachings. It is therefore to be understood that within the scope of the appended claims, the invention
5 be understood that within the scope of the appended claims, the invention may be practiced otherwise than is specifically described herein.

What is claimed is:

-12-

Claims:

1. An electroactive device, comprising:
at least two layers of material, each layer having a length, width and
5 thickness dimension; wherein at least one layer is an electroactive material
and wherein at least one layer is of non-uniform thickness; and
means for bonding the layers to one another.
2. The electroactive device of claim 1, wherein the at least one
10 layer of electroactive material further comprises means to supply electrical
signals across the thickness thereof.
3. The electroactive device of claim 2, wherein the means to
supply electrical signals is at least one electrode positioned on each of the
15 upper and lower surfaces of the at least one layer of electroactive material.
4. The electroactive device of claim 3, wherein the at least one
electrode is a conductive polymer material having elasticity comparable to the
at least one layer of electroactive material and having good adherence to the
20 at least one electroactive material.
5. The electroactive device of claim 2, wherein the applied
amplitude of the electrical signals controls the range of device motion.
- 25 6. The electroactive device of claim 1, wherein the at least one
non-uniform thickness layer enables a controlled contouring of the activated
device.
7. The electroactive device of claim 6, wherein the controlled
30 contouring comprises bending of the activated device.

-13-

8. The electroactive device of claim 6, wherein the controlled contouring comprises torsion of the activated device.

9. The electroactive device of claim 1, wherein the non-uniform
5 thickness of at least one layer is a function of at least one dimension of the layer.

10. The electroactive device of claim 1, wherein the non-uniform thickness of at least one layer is a function of both the length and width of the
10 layer.

11. The electroactive device of claim 1, wherein two or more layers of material are electroactive.

12. The electroactive device of claim 1, wherein one layer of
15 material is non-electroactive.

13. The electroactive device of claim 12, wherein the non-electroactive material is selected from the group consisting of polymers,
20 ceramics, composites and metals.

14. The electroactive device of claim 1, wherein the electroactive material is a material that responds to electrical activation.

15. The electroactive device of claim 1, wherein the electroactive
25 material is selected from the group consisting of polymers, ceramics, and composites.

-14-

16. The electroactive device of claim 1, wherein the electroactive material is an electrostrictive graft elastomer comprising a backbone molecule which is a non-crystallizable, flexible macromolecular chain, and a grafted polymer forming polar graft moieties with backbone molecules, the polar graft moieties having been rotated by an applied electric field and sustained in the rotated state until the electric field is removed.

17. The electroactive device of claim 1, wherein the cross-section of at least one non-uniform layer is defined by a function of the distance along the length of the layer.

18. The electroactive device of claim 1, wherein the cross-section of at least one non-uniform layer is defined by a function of the distance along the width of the layer.

19. The electroactive device of claim 1, wherein the cross-section of at least one non-uniform layer is defined by a function of both the distance along the length of the layer and the distance along the width of the layer.

20. The electroactive device of claim 1, wherein the layers of the device are conformable for use in folded deployable devices.

21. The electroactive device of claim 1, wherein the means for bonding the layers is selected from the group consisting of chemical bonding, physical bonding, mechanical bonding, and biological bonding.

22. An electroactive device as claimed in claim 1, wherein the means for bonding the layers is a chemical bonding means employing a chemical adhesive.

-15-

23. The electroactive device of claim 1, wherein the device itself is a membrane to be deformed.

24. The electroactive device of claim 23, wherein the membrane is
5 a reflector.

25. The electroactive device of claim 1, wherein at least one device is positioned along the surface of a structure to modify the surface's contour.

10 26. The electroactive device of claim 25, wherein the surface to be modified is a skin surface.

27. The electroactive device of claim 26, wherein the device produces traveling waves.
15

28. The electroactive device of claim 25, wherein the surface to be modified is a display panel.

29. The electroactive device of claim 25, wherein the surface to be
20 modified is an optical index layer for a liquid crystal display.

30. The electroactive device of claim 1, wherein at least one device is integrated within the surface of a structure to modify the surface's contour.

25 31. The electroactive device of claim 30, wherein the surface to be modified is a skin surface.

32. The electroactive device of claim 30, wherein the device produces traveling waves.
30

-16-

33. The electroactive device of claim 1, wherein the device performs at least one function selected from the group consisting of shaping, tuning, positioning, controlling and deforming.

34. The electroactive device of claim 1, wherein the device is a component of a micro-electromechanical system.

35. The electroactive device of claim 1, wherein the device is a component of a nano-electromechanical system.

General Information		Study Design		Study Population		Intervention		Outcome Measures		Statistical Analysis			
1	Study Title	2	Study Type	3	Study Location	4	Study Duration	5	Intervention Group	6	Control Group	7	Outcome Measure
8	Study Objectives	9	Study Design	10	Study Population	11	Study Duration	12	Intervention Group	13	Control Group	14	Outcome Measure
15	Study Objectives	16	Study Design	17	Study Population	18	Study Duration	19	Intervention Group	20	Control Group	21	Outcome Measure
22	Study Objectives	23	Study Design	24	Study Population	25	Study Duration	26	Intervention Group	27	Control Group	28	Outcome Measure
29	Study Objectives	30	Study Design	31	Study Population	32	Study Duration	33	Intervention Group	34	Control Group	35	Outcome Measure
36	Study Objectives	37	Study Design	38	Study Population	39	Study Duration	40	Intervention Group	41	Control Group	42	Outcome Measure
43	Study Objectives	44	Study Design	45	Study Population	46	Study Duration	47	Intervention Group	48	Control Group	49	Outcome Measure
50	Study Objectives	51	Study Design	52	Study Population	53	Study Duration	54	Intervention Group	55	Control Group	56	Outcome Measure
57	Study Objectives	58	Study Design	59	Study Population	60	Study Duration	61	Intervention Group	62	Control Group	63	Outcome Measure
64	Study Objectives	65	Study Design	66	Study Population	67	Study Duration	68	Intervention Group	69	Control Group	70	Outcome Measure
71	Study Objectives	72	Study Design	73	Study Population	74	Study Duration	75	Intervention Group	76	Control Group	77	Outcome Measure
78	Study Objectives	79	Study Design	80	Study Population	81	Study Duration	82	Intervention Group	83	Control Group	84	Outcome Measure
85	Study Objectives	86	Study Design	87	Study Population	88	Study Duration	89	Intervention Group	90	Control Group	91	Outcome Measure
92	Study Objectives	93	Study Design	94	Study Population	95	Study Duration	96	Intervention Group	97	Control Group	98	Outcome Measure
99	Study Objectives	100	Study Design	101	Study Population	102	Study Duration	103	Intervention Group	104	Control Group	105	Outcome Measure

-17-

NON-UNIFORM THICKNESS ELECTROACTIVE DEVICE

Abstract

5 An electroactive device comprises at least two layers of material,
wherein at least one layer is an electroactive material and wherein at least
one layer is of non-uniform thickness. The device can be produced in various
sizes, ranging from large structural actuators to microscale or nanoscale
10 devices. The applied voltage to the device in combination with the non-
uniform thickness of at least one of the layers (electroactive and/or non-
electroactive) controls the contour of the actuated device. The effective
electric field is a mathematical function of the local layer thickness.
Therefore, the local strain and the local bending/torsion curvature are also a
mathematical function of the local thickness. Hence the thinnest portion of the
15 actuator offers the largest bending and/or torsion response. Tailoring of the
layer thicknesses can enable complex motions to be achieved.



23351

PATENT TRADEMARK OFFICE

1064

10913 U.S. PTO
09/696526
10/23/00




FIG. 1A










FIG. 1B

000001 92536960








FIG. 4




FIG. 5



National Aeronautics and
Space Administration

NASA Case No.: 16039-1

DECLARATION, POWER OF ATTORNEY AND PETITION - ORIGINAL APPLICATION

As a below named inventor, I hereby declare that: my residence, post office address and citizenship, are stated below next to my name, I believe I am the original, first and sole inventor (If only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled NON-UNIFORM THICKNESS ELECTROACTIVE DEVICE, the specification of which ☒ is attached hereto, ☐ was filed on (Date) _____ as Application Serial No. _____ and was amended on (Date) _____.

I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose to the Patent and Trademark Office all information which is known to me to be material to patentability as defined in 37 CFR §1.56.

I hereby claim the benefit under 35 U.S.C. §120 of any United States application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of 35 U.S.C. §112, I acknowledge the duty to disclose to the Patent and Trademark Office all information known to me to be material to patentability as defined in 37 CFR §1.56 which became available between the filing date of the prior application and the national or PCT international filing date of this application: _____
(Serial No.), _____ (Filing Date), the status of which is
☐ patented, ☐ pending, ☐ abandoned.

I hereby claim foreign priority benefits under Title 35, United States Code, § 119(e) of any United States Provisional applications listed below:
PROVISIONAL APPLICATION NUMBER FILING DATE

60 / 161,113 October 22, 1999
the status of which is
☐ patented, ☒ pending, ☐ abandoned.

POWER OF ATTORNEY: I hereby appoint the following attorney(s) to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith:

<u>LINDA B. B. BLACKBURN</u>	<u>Reg. No. 38,385</u>
<u>KURT G. HAMMERLE</u>	<u>Reg. No. 36,819</u>
<u>ROBIN W. EDWARDS</u>	<u>Reg. No. 39,179</u>
<u>HILLARY W. HAWKINS</u>	<u>Reg. No. 42,235</u>
<u>HELEN M. GALUS</u>	<u>Reg. No. 40,615</u>
<u>SUE H. PALK</u>	<u>Reg. No. 36,422</u>
<u>GARY G. BORDA</u>	<u>Reg. No. 35,455</u>
<u>ALAN J. KENNEDY</u>	<u>Reg. No. 28,625</u>
<u>HARRY LUPULOFF</u>	<u>Reg. No. 31,117</u>

ADDRESS ALL CORRESPONDENCE TO:

Name: ROBIN W. EDWARDS
Address: NASA LANGLEY RESEARCH CENTER
MAIL STOP 212
3 LANGLEY BOULEVARD
HAMPTON, VA 23681-2199

DIRECT TELEPHONE CALLS TO:

Name: ROBIN W. EDWARDS
Telephone: (Set out complete number to be dialed from USPTO):
757-864-3230
757-864-3522

Further, as a named inventor I certify that the Government of the United States of America, as represented by the Administrator of the National Aeronautics and Space Administration, has x an assignment in, or _ license to the invention set forth in this application and has the irrevocable right to practice this application and to receive the patent.

Wherefore, I pray that Letters Patent be granted to me for this invention or discovery described and claimed in the foregoing specification and claims, and I hereby subscribe my name to the foregoing specification, claims, power of attorney and this petition.

I hereby declare that all statements made herein of my own knowledge are true and that - statements made on information and belief are believed to be true; and further that these, statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under 18 U.S.C. §1001; and that such willful false statements may jeopardize the validity of the application or any patent issuing thereon.

FULL NAME OF INVENTOR	LAST SU	FIRST Ji	MIDDLE OR INITIAL (nmi)
RESIDENCE AND CITIZENSHIP	CITY Highland Park	STATE OR FOREIGN COUNTRY New Jersey	COUNTRY OF CITIZENSHIP U.S.
POST OFFICE	STREET NO. AND NAME 803C Donaldson Street	CITY AND STATE OR (COUNTRY) Highland Park, New Jersey	ZIP CODE 08904
SIGNATURE			DATE

FULL NAME OF INVENTOR	LAST HARRISON	FIRST Joycelyn	MIDDLE OR INITIAL S.
RESIDENCE AND CITIZENSHIP	CITY Hampton	STATE OR FOREIGN COUNTRY Virginia	COUNTRY OF CITIZENSHIP U.S.
POST OFFICE	STREET NO. AND NAME 31 Gunter Court	CITY AND STATE OR (COUNTRY) Hampton, Virginia	ZIP CODE 23666
SIGNATURE			DATE

FULL NAME OF INVENTOR	LAST	FIRST	MIDDLE OR INITIAL
RESIDENCE AND CITIZENSHIP	CITY	STATE OR FOREIGN COUNTRY	COUNTRY OF CITIZENSHIP
POST OFFICE	STREET NO. AND NAME	CITY AND STATE OR (COUNTRY)	ZIP CODE
SIGNATURE			DATE